

Lab # Sample	Cu_ppm	Ag_ppm	Litho 1	Texture 1	Texture 2	Mx	Type	Certificat nber	Easting*	Northing*
S750514	9510	290					STANDARD 603B	VO22220224		
S750515	4.5		TL	YX		MC	RAINURE	VO22220224	349589	5386031
S750516	5.3		S7	YX	M15	MC	RAINURE	VO22220224	349606	5386040
S750517	8.3		S7A	YX	M15	PY	Grab-Sample	VO22225485	347960	5381714
S750518	1						Blank	VO22225485		
S750520	210		TL	MG		MC	Grab-Sample	VO22237818	347890	5386899
S750521	668		S7	YY		MC, CL	Grab-Sample	VO22237818	349651	5386067
S750522	143.5		S7	YY	M15	PY, MC	Grab-Sample	VO22237818	349653	5386063
S750523	215		S6A	SA		MC	Grab-Sample	VO22237818	349665	5386075
S750524	6.5		S7	YY	M15	MC	Grab-Sample	VO22237818	349632	5386053
S750525	3.3		S4-EP			MC	Grab-Sample	VO22237818	349631	5386052
S750526	1.1						Blank	VO22237818		
S750527	11.1		S1			MC	Grab-Sample	VO22240703	349597	5386035
S750528	15.8		V3B	GT		MC	Grab-Sample	VO22240703	344241	5388153
S750529	40		V3B	GM			BLOC	VO22240703	344238	5388247
S750530	14.6		V3A	PO	VE		Grab-Sample	VO22240703	342386	5386298
S750531	9.1		V3B	MG	GF	MC, CL	BLOC	VO22240703	338436	5378975
S750532	8.8		TL	MG		MC	Grab-Sample	VO22240703	338734	5378246
S750533	582		S4-EP	MG	MA	MC	Grab-Sample	VO22240703	338712	5378934
S750534	390		S6A	SA			Grab-Sample	VO22251580	349642	5386059
S750535	109		S8A	SA			Grab-Sample	VO22251580	349642	5386057
S750536	4.5		S7	GE	XG?	MN	Grab-Sample	VO22251580	349650	5386062
S750537	128.5		S7	GE	XG?	MN	Grab-Sample	VO22251580	349651	5386065
S750538	264		S7	YY	M15	PY, MC	Grab-Sample	VO22251580	349653	5386067
S750539	17.5						RAINURE	VO22251580	347600	5381723
S750540	3.2						Blank	VO22251580		
S750541	194						RAINURE	VO22251580	347596	5381733
S750542	24.9						RAINURE	VO22251580	347596	5381733
S750543	124						RAINURE	VO22251580	347596	5381733
S750544	132.5						RAINURE	VO22251580	347596	5381733
S750545	18.6		V3B	PO		CL, MC	Grab-Sample	VO22251580	340843	5379803
S750546	125.5		V3B	VE		CL, MC	Grab-Sample	VO22251580	340760	5379575
S750547	57.4		V3B			CL, MC	Grab-Sample	VO22251580	340931	5380012



Technical data of Native Copper project samples, work 2022. 1844 Resources Inc.

Lab # Sample	Cu_ppm	Ag_ppm	Litho 1	Texture 1	Texture 2	Mx	Type	Certificat nber	Easting*	Northing*
S750548	20400	2.43	S4-EP			MC	BLOC	VO22251580	340863	5379950
S750549	2160	0.58	S4-EP			MC	BLOC	VO22251580	341141	5379827
S750550	55.1		V3B	GT	VE	MC	Grab-Sample	VO22251580	341706	5379886
X340016	1.5		S4-S7	YX	M15		Grab-Sample	VO22225485	347741	5381697
X340017	7.5		S1-EP		M15		Grab-Sample	VO22225485	347797	5381694
X340018	105		S7A	MA		PY	Grab-Sample	VO22225485	347791	5381702
X340019	2.3		S7	MA	M15	PY	Grab-Sample	VO22225485	348154	5386647
X340020	3.7		S7	YX	M15	MC	Grab-Sample	VO22225485	345453	5387668
X340021	2.6		S7	YX	M15		Grab-Sample	VO22225485	345445	5387700
X340022	283		V3B	AM	MG	MC	Grab-Sample	VO22225485	349295	5386439
X340023	30.3		V3B	GT			Grab-Sample	VO22220224	349293	5386402
X340024	54.8		V3B	GT			Grab-Sample	VO22220224	349293	5386382
X340025	21.4		V3B	PO	MG		Grab-Sample	VO22220224	349289	5386368
X340026	0.9						Blanck	VO22220224		
X340027	58	0.11	S7A	YX	M15	PY, MC	Grab-Sample	VO22220224	347795	5387132
X340028	191	0.66	S7A	YX	M15	PY	Grab-Sample	VO22220224	347792	5387133
X340029	3.6		S7	YX	M15		Grab-Sample	VO22220224	349471	5386111
X340030	12.6		S7	YX	M15		Grab-Sample	VO22220224	349472	5386107
X340031	2460	1.34	S7	YX	M15		Grab-Sample	VO22220224	349485	5386115
X340032	50.7		S1-EP			HM	Grab-Sample	VO22220224	349483	5386111
X340033	8		TU	YX		MC	Grab-Sample	VO22220224	349487	5386124
X340034	28.2		S7	YX	M15		Grab-Sample	VO22220224	349483	5386113
X340035	24.1		S8A		M15		Grab-Sample	VO22220224	349483	5386116
X340036	6.2		S7	YX	M15		Grab-Sample	VO22220224	349485	5386118
X340037	322		TU	YX		MC	Grab-Sample	VO22220224	349487	5386122
X340038	7		S8A		M15		RAINURE	VO22220224	349586	5386029
X340039	12		S1-EP			MC	RAINURE	VO22220224	349590	5386029
X340040	2.1						Blanck	VO22220224		
X340041	6.7		TL	YX		MC	RAINURE	VO22220224	349590	5386029
X340042	3.2		S8A		M15	MC	RAINURE	VO22220224	349590	5386029
X340043	13.9		S1			MC	RAINURE	VO22220224	349597	5386034
X340044	7.1		S1			MC	RAINURE	VO22220224	349597	5386034
X340045	7.2		TL	YX		MC	RAINURE	VO22220224	349597	5386034



Lab # Sample	Cu_ppm	Ag_ppm	Litho 1	Texture 1	Texture 2	Mx	Type	Certificat nber	Easting*	Northing*
X340046	7.7		S7	YX	M15		RAINURE	VO22220224	349601	5386037
X340047	17.5		S6A	MG	M15		Grab-Sample	VO22220224	347890	5386855
X340048	33.8		TL TY		M15	CL	Grab-Sample	VO22220224	349996	5385983
X340049	34.9		TL TY		M15	CL	Grab-Sample	VO22220224	349996	5385987
X340050	58.3		TL TY		M15	CL	Grab-Sample	VO22220224	349997	5385991
X341901	60.8	0.36	S7			PY	Grab-Sample	VO22280537	332803	5384531
X341902	36		V3B	VE	AM-QZ-CL		Grab-Sample	VO22280537	327912	5375313
X341903	5.8		V3A	GF		PY	Grab-Sample	VO22280537	328293	5374589
X341904	15.5		V3B	PO	AM-CL		Grab-Sample	VO22280537	327848	5375799
X341906	14		V3A	GF		PY	Grab-Sample	VO22280537	324947	5375862
X341907	18		S4-EP				Grab-Sample	VO22280537	340367	5384319
X341908	848		V3B	PO			Grab-Sample	VO22280537	340372	5384313
X341909	14.7		S4-EP				Grab-Sample	VO22280537	340712	5384912
X341910	96.4		V3B	GF	VE		Grab-Sample	VO22280537	340711	5384907
X341911	71.2		V3B	PO			Grab-Sample	VO22280537	337273	5382268
X341912	31.7		V3B	PO	VE		Grab-Sample	VO22280537	337263	5382243
X341913	15.6		V3B	GF	AM-QZ		Grab-Sample	VO22280537	337111	5381962
X341914	41.8		V3B	PO		PY	Grab-Sample	VO22280537	336431	5382107
X341915	73.8		V3B	PO	AM-CL, AM-QZ	PY	Grab-Sample	VO22280537	335621	5381769
X341916	19.9		V3B	PO	AM-CL, AM-QZ	PY	Grab-Sample	VO22280537	335710	5381715
X341917	1.5						Blanck	VO22280537		
X341918	254		V3B	GF		PY	Grab-Sample	VO22280537	335786	5381687
X341951	1125	0.52	VN	FAILLE		MC	Grab-Sample	VO22251580	344028	5380920
X341952	55		S1-EP	SA		CL	Grab-Sample	VO22251580	343633	5381614
X341953	5		S1-EP	SA		CL, MC	Grab-Sample	VO22251580	347944	5381717
X341954	46.3		S4-EP			CL, MC	Grab-Sample	VO22251580	340988	5379877
X341955	27		S4-EP			CL, MC	Grab-Sample	VO22251580	343676	5381461
X341956	29.6		S4-EP			CL, MC	Grab-Sample	VO22251580	343672	5381452
X341957	2.2						Blanck	VO22251580		
X341958	46		S4-EP				Grab-Sample	VO22251580	343569	5381497
X341959	46.6		FAILLE			CL	Grab-Sample	VO22251580	349682	5386083
X341960	16.6		TU			CL, MC	Grab-Sample	VO22251580	349709	5386100
X341961	60.7		V3B	PO	VE	CL, MC	Grab-Sample	VO22251580	340802	5379451



Lab # Sample	Cu_ppm	Ag_ppm	Litho 1	Texture 1	Texture 2	Mx	Type	Certificat nber	Easting*	Northing*
X341962	34.5		S6A ou TU	SA			Grab-Sample	VO22251580	338476	5378865
X341963	29.2		S4 ou TL				Grab-Sample	VO22251580	338478	5378864
X341964	42.2		S4-EP	SA		MC	Rainure	VO22280537	338467	5378796
X341965	347		S4-EP	SA			Rainure	VO22280537	338467	5378796
X341966	70.6		S4-EP	SA			Grab-Sample	VO22280537	338466	5378792
X341967	30.8		S4-EP	SA		MC	Grab-Sample	VO22280537	338466	5378773
X341968	364		S4-EP	SA		MC	Grab-Sample	VO22280537	338468	5378815
X341969	1115	0.56	S7	YY		MC	Grab-Sample	VO22280537	347596	5381734
X341970	211		S7	YY		MC	Rainure	VO22280537	347596	5381733
X341971	4.1						Blanck	VO22280537		
X341972	385	0.18	S7	YY		MC	Rainure	VO22280537	347595	5381735
X341973	60.4		V3B	PO	AM-CL	MC	Grab-Sample	VO22280537	341448	5385693
X341974	12		V3B	PO	AM-CL	MC	Grab-Sample	VO22280537	341453	5385704
X341975	341		V3B	PO	AM-CL	MC, AZ	Grab-Sample	VO22280537	341445	5385697
X341976	32.1		V3B	PO	AM-CL	MC	Grab-Sample	VO22280537	342415	5386336
X341977	15.9		V3B	PO	AM-CL	MC	Grab-Sample	VO22280537	342345	5386262
X341978	31.5		V3B	PO	AM-CL	PY	Grab-Sample	VO22280537	341559	5386579
X341979	86.9		V3B	GF		CL, MC	Grab-Sample	VO22280537	344558	5380960
X341980	61.7		V3B	GF		MG, PY	Grab-Sample	VO22280537	344559	5380815
X341981	87.1		V3B	PO		MC	Grab-Sample	VO22280537	344078	5380875
X341982	48.6		V3B	BR			Grab-Sample	VO22280537	346540	5380732
X341983	50.3		V3B	VE		GO	Grab-Sample	VO22280537	346538	5380714
X341984	55.9		V3B	PO	AM		Grab-Sample	VO22280537	346417	5380977
X341986	68		V3B	BR			Rainure	VO22280537	341439	5385694
X341987	95.3		V3B	BR			Rainure	VO22280537	341439	5385696
X341988	48.8		V3B				Rainure	VO22280537	341443	5385693
X341989	48.6		V3B				Rainure	VO22280537	341443	5385693
X341990	83.4		V3B				Rainure	VO22280537	341447	5385691
X341991	80.6		V3B				Rainure	VO22280537	341447	5385691
X341992	59.6		V3B				Rainure	VO22280537	341451	5385692
X341993	57.8		V3B				Rainure	VO22280537	341450	5385692
X341994	87.7		V3B				Rainure	VO22280537	341451	5385692
X341995	66.2		V3B				Rainure	VO22280537	341453	5385688



Technical data of Native Copper project samples, work 2022. 1844 Resources Inc.

Lab # Sample	Cu_ppm	Ag_ppm	Litho 1	Texture 1	Texture 2	Mx	Type	Certificat nber	Easting*	Northing*
X341996	112		V3B				Rainure	VO22280537	341453	5385688
X341997	2.2						Blanck	VO22280537	341456	5385701
X341998	37.8		V3B				Rainure	VO22280537	341456	5385701
X341999	96		V3B				Rainure	VO22280537	341457	5385699
X342000	69.4	0.14	V3B	PO		PY	Grab-Sample	VO22280537	332803	5384534

* NAD83Zone20

